

|          |   |                     |
|----------|---|---------------------|
| Product: | <b>ROCKWOOL® Stone wool</b>                 | <b>P.D.S<br/>21</b> |
| Type:    | <b>LIGHT-WEIGHT SEMI-RIGID SLAB</b>         |                     |
| Name:    | <b>RockTech S 100 (for use up to 300°C)</b> | Page 1 of 4         |

### Description

ROCKWOOL® RockTech S 100 is a high quality resin-bonded light-weight semi-rigid mineral wool slab with excellent thermal, acoustic and fire safety properties.

Applications for RockTech S 100 can be used for low temperature thermal insulation and for general acoustic applications.

Standard Sizes (mm)

| Thickness | Dimensions | Slab Per Pack |
|-----------|------------|---------------|
| 25        | 1200 x 600 | 12            |
| 38        | 1200 x 600 | 8             |
| 50        | 1200 x 600 | 6             |
| 75        | 1200 x 600 | 4             |
| 100*      | 1200 x 600 | 3             |

\* not a stock item

Special sizes and facings are available to order but may be subject to minimum production quantity requirements.

### Product Performance and Properties

**Density:** > 55 kg/m³ (nominal):- being delivered density according to ASTM C612 - 93

**Service Temperature:** Maximum continuous service temperature on plain surface 300°C (662°F) according to ASTM C411.

**Thermal Conductivity (typical data):** 0.036 W/mK at 23°C (ASTM C 518 – 1991).

## PRODUCT DATA SHEET

|                |              |
|----------------|--------------|
| REVISION:      | 4            |
| DATE OF ISSUE: | Nov 02       |
| CHKD:          | BH APPV: IRS |

|          |   |                     |
|----------|---|---------------------|
| Product: | <b>ROCKWOOL® Stone wool</b>                 | <b>P.D.S<br/>21</b> |
| Type:    | <b>LIGHT-WEIGHT SEMI-RIGID SLAB</b>         |                     |
| Name:    | <b>RockTech S 100 (for use up to 300°C)</b> | Page 2 of 4         |

**Corrosion Resistance:** Stone wool is chemically neutral and will neither  
**Chemical Neutrality:** cause nor promote corrosion.

**Corrosion Resistance:** Stone wool has a very low content of water leachable  
**Water Leachable Chlorides:** chloride, less than 6 ppm so it can be safely used on  
 austenitic stainless steel. Meets the requirements for use  
 over stainless steel in accordance with ASTM C795.

**Fire:** Non-combustible when tested according to international  
 standards eg. ASTM E-136-82, DIN 4102, BS476 Pt4-  
 1970, ISO R 1182, AS 1530.1.

**Moisture Resistance Water:** Highly water repellent, non-hygroscopic and non-capillary.  
 The water repellency is in accordance with BS 2972 (total  
 immersion) is >96% (vol.). RockTech S 200 is water  
 repellent in accordance with AGI Q 136.

**Moisture Resistance Vapour Diffusion:** Water vapour diffusion resistance factor of  $\mu = 1.3$ . This  
 low value means that water can pass through and cool  
 without condensing.

**Moisture Resistance:** Absorbs very little water from the air. Tests show at  
**Absorption from the air:** relative humidity of 90% for 30 days the hygroscopic water  
 content is around .004 volume per cent. The water vapour  
 absorption (vapor sorption) in accordance with ASTM C110  
 4/C 1104 m is  $\pm 0.02\%$  (vol).

**Moisture Resistance Capillarity:** Stone wool fibres and fibre coating repels water and  
 prevents capillarity.

**Melting Point:** Melting point of the stone wool fibre is over 1000°C  
 (1800°F)

|                           |                       |
|---------------------------|-----------------------|
| <b>PRODUCT DATA SHEET</b> | REVISION: 4           |
|                           | DATE OF ISSUE: Nov 02 |
|                           | CHKD: BH APPV: IRS    |

|          |   |                           |
|----------|---|---------------------------|
| Product: | <b>ROCKWOOL® Stone wool</b>                 | <b>P.D.S</b><br><b>21</b> |
| Type:    | <b>LIGHT-WEIGHT SEMI-RIGID SLAB</b>         |                           |
| Name:    | <b>RockTech S 100 (for use up to 300°C)</b> | Page 3 of 4               |

**Specific Heat:** Stone wool specific heat factor is 0.84 kJ/kg per degree centigrade.

**Calorific Value:** Stone wool has a low organic matter content giving a low caloric value of around 600 kJ/kg.

**Biological Properties:** Stone wool contains no nutrients and therefore provides no basis for growth of fungi, moulds or bacteria, nor does it attract insects, rodents or vermin.

**Acoustic Properties:** The stone wool base material when measured according to ISO 354 and applied directly to the wall surface at a thickness of 50 mm gives the following:

| H <sub>z</sub> | 125  | 250  | 500  | 1000 | 2000 | 4000 |
|----------------|------|------|------|------|------|------|
| Coeff α S      | 0.23 | 0.74 | 1.14 | 1.11 | 1.05 | 1.05 |

**Durability:** Stone wool has been proven in services for over 50 years in all types of exposure and as such will give effective protection for the lifetime of the equipment they insulate.

**Compatibility:** Stone wool is compatible with all materials which it is likely to come into contact in normal industrial and building applications.

**Environment:** Stone wool presents a very effective ecological profile in all elements of manufacture, recycling use, service life and energy efficiency of material. No CFC's or HCFC's are used in its manufacture.

|                           |                |              |
|---------------------------|----------------|--------------|
| <b>PRODUCT DATA SHEET</b> | REVISION:      | 4            |
|                           | DATE OF ISSUE: | Nov 02       |
|                           | CHKD:          | BH APPV: IRS |

|          |   |                           |
|----------|---|---------------------------|
| Product: | <b>ROCKWOOL® Stone wool</b>                 | <b>P.D.S</b><br><b>21</b> |
| Type:    | <b>LIGHT-WEIGHT SEMI-RIGID SLAB</b>         |                           |
| Name:    | <b>RockTech S 100 (for use up to 300°C)</b> | Page 4 of 4               |

### Health & Safety

**RockTech S is NOT CLASSIFIED as HAZARDOUS according to NOHSC criteria as a consequence of the following events and conclusions about the health effects of long term occupation exposure to mineral wool insulation products.**

- Over 50 years of extensive health research on ROCKWOOL® products in Europe has resulted in the scientific conclusion that there are no long term health problems from using rock(stone)wool.
- In March 1995 the UK Health and Safety Executive concluded that rock(stone)wool should not be classified as a potential carcinogen.
- Under note Q of the National Occupational health and Safety Commission (NOHSC) publication "List of Designated Hazardous Substances" (NOHSC; 1005-1999) the classification of NON-CARCINOGENIC is to apply.
- Under the European Union Criteria set out in 67/548/EEC a classification of CARC, Cat O applies, ie; "Not classifiable for carcinogenicity."
- Under World Health Organisation (WHO) and its Monographs Programme of the International Agency for Research on Cancer (IARC) it has been concluded that, "Rock (stone) wool are now considered not classifiable as to carcinogenicity to humans (Group 3),

It is recommended that for the handling and installation of ROCKWOOL products the internationally recognised Safety Data Sheet be followed. This is available from Australasian Insulation Supplies Pty Ltd.

### Technical Advice and Thermal Calculation Service:

Heat transfer calculation for ROCKWOOL stone wool insulation systems in thermal design is readily available. AIS technical advisers are ready to give help and advice on any matter connected with insulation or products manufactured by ROCKWOOL

For further information and technical advice on insulation contact:

## PRODUCT DATA SHEET

|                |                     |
|----------------|---------------------|
| REVISION:      | <b>4</b>            |
| DATE OF ISSUE: | <b>Nov 02</b>       |
| CHKD:          | <b>BH APPV: IRS</b> |